

MOX-Report No. 59/2024

Easy-to-use formulations based on the homogenization theory for vascular stent design and mechanical characterization

Carbonaro, D.; Ferro, N.; Mezzadri, F.; Gallo, D.; Audenino, A.; Perotto, S.; Morbiducci, U.; Chiastra, C.

> MOX, Dipartimento di Matematica Politecnico di Milano, Via Bonardi 9 - 20133 Milano (Italy)

mox-dmat@polimi.it

https://mox.polimi.it

Easy-to-use formulations based on the homogenization theory for vascular stent design and mechanical characterization

Dario Carbonaro¹, Nicola Ferro², Francesco Mezzadri³, Diego Gallo¹, Alberto Audenino¹, Simona Perotto², Umberto Morbiducci¹, Claudio Chiastra¹

September 4, 2024

¹ Polito^{BIO}MED Lab – Department of Mechanical and Aerospace Engineering Politecnico di Torino, Torino, Italy

> ² MOX – Department of Mathematics Politecnico di Milano Piazza L. da Vinci, 32, I-20133 Milano, Italy

> ³ Department of Engineering "Enzo Ferrari" University of Modena and Reggio Emilia, Modena, Italy

Abstract

Vascular stents are scaffolding structures implanted in the vessels of patients with obstructive disease. Stents are typically designed as cylindrical lattice structures characterized by the periodic repetition of unit cells. Their design, including geometry and material characteristics, influences their mechanical performance and, consequently, the clinical outcomes. Computational optimization frameworks have proven to be effective in assisting the design phase of vascular stents, facilitating the achievement of enhanced mechanical performances. However, the reliance on time-consuming simulations and the challenge of automating the design process limit the number of design evaluations and reduce optimization efficiency. In this context, a rapid and automated method for the mechanical characterization of vascular stents is presented, taking the stent geometry, conceived as the periodic repetition of a unit cell, and material as input and providing the mechanical response of the stent as output.

Vascular stents were assumed to be thin-walled hollow cylinders sharing the same macroscopic geometrical characteristics as the cylindrical lattice structure but composed of an anisotropic homogenized material. Homogenization theory was applied to average the microscopic inhomogeneities at the stent unit cell level into a homogenized material at the macroscale, enabling the calculation of the associated homogenized material tensor. Analytical formulations were derived to relate the stent mechanical behavior to the homogenized stiffness tensor, considering linear elastic theory for thin-walled hollow cylinders and three loading scenarios of relevance for vascular stents: radial crimping; axial traction; torsion. Validation was conducted by comparing the derived analytical formulations with results obtained from finite element analyses on typical stent designs.

Homogenized stiffness tensors were computed for the unit cells of three stent designs, revealing insights into their mechanical performance, including whether they exhibit auxetic behavior. The derived analytical formulations were successfully validated with finite element analyses, yielding low relative differences in the computed values of foreshortening, radial, axial and torsional stiffnesses for all three stents.

The proposed method offers a rapid, fully automated procedure that facilitates the assessment of the mechanical behavior of vascular stents and is suitable for effective integration into computational optimization frameworks.

Keywords: Medical device design; auxetic stent; lattice structure; computational structural mechanics; finite element method; shape optimization; topology optimization.

1) Introduction

Vascular stents are minimally invasive medical devices commonly used in the treatment of obstructive diseases [1]. Initially, stents undergo a crimping procedure (radial compression) for insertion into a catheter. They are then deployed at the obstruction site in the vessel, with or without balloon expansion [2], to provide structural support to the vessel wall and prevent post-interventional vessel blockage [1]. Technically, vascular stents are designed as cylindrical lattice structures, typically characterized by the periodic repetition of a unit cell [1]. They come in various shapes, sizes, and materials depending on the target implantation site, whether it be the coronary, carotid, femoral arteries, or other locations [3–5].

The design of vascular stents, including cell geometry and material characteristics, directly influences the mechanical response of the devices and, consequently, the clinical outcomes [4–7]. Specifically, vascular stents require adequate radial stiffness to prevent vessel recoil while avoiding tissue damage [8]. Moreover, once implanted, they undergo mechanical loads such as radial loading, axial compression and tension, torsion, and bending, which vary according to the implantation site and tissue composition of the target vessel [9–11]. The mechanical response of a stent to this multifaceted loading condition determines the device-vessel interaction, which is a key design target for enhancing both the effectiveness and safety of the treatment, as well as for improving short- and long-term outcomes.

Computational modeling has proven effective in assisting the design and development of vascular stents, facilitating the achievement of designs with enhanced mechanical performances while reducing the need for prototyping and experimental testing [12]. Several computational design optimization frameworks have been developed for this purpose, employing either shape or topology optimization approaches to assess and balance competing design objectives, with the ultimate goal of enhancing clinical outcomes [6,13–29]. These optimization approaches involve iteratively evaluating the

mechanical response of numerous stent designs. However, this iterative process is challenging to automate and typically relies on time-consuming structural mechanics analysis, thereby limiting the number of designs that can be evaluated and reducing the efficiency of the optimization frameworks.

In this context, this study introduces a method for the mechanical characterization of vascular stents through the analysis of periodic unit cell geometries. The proposed method exploits the homogenization theory combined with the linear elastic theory for thin-walled hollow cylinders to derive simple analytical formulations that relate specific stiffness tensor components to the mechanical behavior of the device. This method can be adopted to compare the mechanical responses expected from different stent cell unit designs and can be easily integrated into automated optimization frameworks to assist the design of new stents with improved mechanical performance.

2) Methods

The workflow of the proposed method for the evaluation of the mechanical performance of vascular stents with different unit cell geometry is outlined in Fig. 1. In brief, the method takes the stent geometry, conceived as a periodic repetition of a unit cell, as input and provides a robust estimate of the foreshortening, radial, axial, and torsional stiffness values of the device as output. To achieve this, analytical formulations describing vascular stents mechanical behaviour are derived under three distinct loading conditions (i.e., radial compression, axial traction and torsion) using stiffness matrix components obtained combining the homogenization theory applied to the stent unit cell with the linear elastic theory for thin-walled hollow cylinders. Section 2.1 describes the general characteristics of the stent geometry and material. Section 2.2 details the evaluation of the homogenized stiffness tensor associated with the stent unit cell. Section 2.3 describes the assessment of the stent's mechanical properties based on the

homogenized stiffness tensor and on the macroscopic geometric features of the device. Finally, Section 2.4 outlines the validation of the proposed framework through comparisons with finite element (FE) simulations, where the loading conditions of interest are applied to vascular stents featuring different unit cell geometries.



Fig. 1. Workflow of the method for the mechanical characterization of vascular stents. (i) Input: stent geometry conceived as the repetition of a unit cell (micro-scale geometric features) with specific values of radius R_0 , length l_0 , and thickness *t* (macro-scale geometric features), and material, as detailed in Section 2.1; (ii) Method for the mechanical characterization: evaluation of the homogenized material tensor corresponding to the investigated unit cell geometry, as detailed in Section 2.2, and application of linear elastic theory for thin-walled hollow cylinders under three distinct loading conditions, namely radial compression, axial traction and torsion, as detailed in Section 2.3; (iii) Output: evaluation of the mechanical response, including foreshortening *f*, radial stiffness K_R , axial stiffness K_A , and torsional stiffness K_T , as detailed in Section 2.3.

2.1) Vascular stent: geometry and mechanical response

Considering a cylindrical coordinate system, the typical geometry of a vascular stent can be conceptualized as comprising a 2D stent unit cell of constant thickness *t*, which is repeated periodically N_z times along the *z*-axis (i.e., the axial direction) and N_θ times along the θ -axis (i.e., the circumferential direction) to form the whole axisymmetric lattice structure (Fig. 2). Given the stent radius R_0 and the aspect ratio $\alpha = w/h$ of the unit cell (Fig. 2(a)), where w represents the width and h denotes the height of the unit cell, respectively, the length of the stent l_0 can be determined according to the formula

$$l_0 = N_z w = N_z \alpha h = 2\pi R_0 \alpha \frac{N_z}{N_\theta}.$$
(1)

The mechanical response of vascular stents is determined by the associated design features, which include what we define (i) macroscopic quantities (i.e., R_0 , l_0 , and t), (ii) microscopic quantities (i.e., α , and the unit cell topology), and (iii) the mechanical properties of the material employed for the device manufacturing. To account for all these design features within stent performance analysis in a computationally affordable way, the homogenization theory is applied to a 2D unit cell of the stent. To do that, vascular stents are assumed to be thin-walled hollow cylinders, macroscopically defined by R_0 , l_0 , and t, and composed of an anisotropic homogenized material. This material is obtained by appropriately merging the microscopic quantities α and unit cell topology of the 2D unit cell (Fig. 2(c)) with the mechanical properties of the manufacturing material.



Fig. 2. (a) Stent unit cell, with indication of the local coordinate system *I* and *2*; *w* and *h*: width and height of the unit cell, respectively. (b) Vascular stent, with indication of the global cylindrical coordinate system. N_z and N_{θ} : number of periodic repetitions of the unit cell in *z* and θ direction, respectively; *t*: thickness of the stent; l_{θ} : length of the stent; R_{θ} , radius of the stent, considering the radius of the inner and outer surfaces be equal to $R_{\theta} - t/2$ and $R_{\theta} + t/2$, respectively. (c) Homogeneous thin-walled hollow cylinder with homogenized anisotropic material, with the same R_{θ} , l_{θ} and *t*.

2.2) Evaluation of the homogenized material tensor

Homogenization theory allows to rigorously map a complex multiscale description of the device into a simplified one where the microscopic inhomogeneities at the unit cell scale are homogenized into a new material at the macroscale (Fig. 2). To describe the homogenization technique in mathematical terms, it is assumed that the macroscopic medium under analysis, $\Omega \subset \mathbb{R}^2$, is the assembly of periodic repetitions of a microscopic unit cell, $Y \subset \mathbb{R}^2$, whose area |Y| is considerably lower than the area $|\Omega|$ of the whole medium. Unit cells are not homogeneous, and this reflects in the microscopic variations in the physical behavior characterizing the macroscopic medium. The homogenization procedure removes such variations at the microscale, although inheriting the associated effect at the homogenized scale. With a view to the characterization of the mechanical properties of the stent, the reference physical model is the equilibrium elasticity equation at the macroscale

$$-\nabla \cdot \sigma(\boldsymbol{u}) = \boldsymbol{0} \quad \text{in } \Omega, \tag{2}$$

where $\boldsymbol{u} \in \mathbb{R}^2$ is the displacement vector and σ is the stress tensor.

In a linear regime, the stress tensor is related to the strain tensor $\varepsilon(\mathbf{u}) = (\nabla \mathbf{u} + \nabla \mathbf{u}^T)/2$ through the relation

$$\sigma(\boldsymbol{u}) = E\varepsilon(\boldsymbol{u}) = \begin{bmatrix} E_{1111} & E_{1122} & E_{1112} \\ E_{2211} & E_{2222} & E_{2212} \\ E_{1211} & E_{1222} & E_{1212} \end{bmatrix} \varepsilon(\boldsymbol{u}),$$
(3)

where the so-called stiffness tensor $E = [E_{ijkl}]$, with $ij, kl \in \{11, 22, 12\}$, is a symmetric fourth-order tensor depending on the considered material constituting the medium (i.e., Young's modulus and Poisson's ratio). Notice that Eq. (2) must be completed with appropriate boundary conditions on $\partial\Omega$, and that Eq. (3) is valid at both the macroscale (in Ω) and the microscale (in *Y*). Homogenization converts Eq. (3) to the homogenized counterpart

$$\sigma(\boldsymbol{u}) = E^H \varepsilon(\boldsymbol{u}),\tag{4}$$

where the homogenized stiffness tensors E^H links the mechanical response at the microscale Y to the macroscale Ω . In more detail, the stiffness tensor E^H can be obtained through an asymptotic expansion of the displacement field \boldsymbol{u} in Eq. (2) [30]. In practice, this leads to solve the following differential problem in the periodic unit cell Y: being $U_P = [H_P^1(Y)]^2$ the vector space of periodic variations belonging to the Sobolev space $H^1(Y)$, and $\boldsymbol{u}^{0,ij}$ denoting three independent test displacements, with $u^{0,11} = [x, 0]^T$, $u^{0,22} = [0, y]^T$, $u^{0,12} = [y, 0]^T$, find the microscopic variations $u^{*,ij} \in U_P$, with $ij = \{11,22,12\}$ such that $\forall v \in U_P$

$$\int_{Y} \sigma(\boldsymbol{u}^{*,ij}): \varepsilon(\boldsymbol{\nu}) dY = \int_{Y} \sigma(\boldsymbol{u}^{0,ij}): \varepsilon(\boldsymbol{\nu}) dY.$$
⁽⁵⁾

The solutions to Eq. (5) allow for the explicit expression of the homogenized stiffness tensor $E^{H} = [E_{ijkl}^{H}]$, where

$$E_{ijkl}^{H} = \frac{1}{|Y|} \int_{Y} \left[\sigma \left(\boldsymbol{u}^{0,ij} \right) - \sigma \left(\boldsymbol{u}^{*,ij} \right) \right] : \left[\varepsilon \left(\boldsymbol{u}^{0,ij} \right) - \varepsilon \left(\boldsymbol{u}^{*,ij} \right) \right] dY.$$
(6)

Eqs. (5) and (6) are commonly solved numerically. To this aim, a FE scheme based on adapted simplicial meshes and linear polynomials is adopted in this study to approximate variations $u^{*,ij}$ (namely to compute the stiffness tensor E^H) in an accurate and efficient manner. We refer to [31] for the homogenization theory basics, and to recent literature for applications of adapted meshes to the computation of E^H [32–34].

2.3) Assessment of stent mechanical response

The mechanical response of vascular stents is here characterized considering three distinct loading scenarios (Fig. 3), namely (i) radial compression, (ii) axial tension, and (iii) torsion, enabling the evaluation of the device foreshortening f, radial stiffness K_R , axial stiffness K_A , and torsional stiffness K_T . The quantities K_R and f are evaluated by emulating radial compression (Fig. 3(a)) to replicate the radial crimping test, a standard procedure which mimics the loading conditions experienced by vascular stents when inserted into a catheter prior to deployment in the vessel [35,36]. The quantities K_A and K_T are evaluated by emulating axial traction and torsion tests, respectively (Fig. 3(b) and (c)).



Fig. 3. Investigated loading scenarios with indication of the assigned boundary conditions. (a) Radial compression: a displacement u_r^* is assigned in the radial (*r*) direction; accordingly, *f* and K_R are evaluated; (b) Axial traction: a displacement u_z^* is assigned in the axial (*z*) direction at one extremity of the cylinder, while the other extremity (black line) is fixed in the *z* direction; accordingly, K_A is evaluated; (c) Torsion: a rotation φ^* is imposed on one extremity of the cylinder, while the other extremity (black line) is fixed in the circumferential (θ) direction; accordingly, K_T is evaluated.

The derivation of the analytical formulations expressing the mechanical response of the stents is performed by introducing some simplifying assumption. In detail, due to the small thickness *t* of the unit cells compared to R_0 and l_0 , the axisymmetric nature of vascular stents, and the boundary conditions characterizing the three loading scenarios, a state of plane stress is assumed with reference to the cylindrical coordinate system (Fig. 4). Moreover, since the radial crimping test aims to uniformly compress the vascular stent in the radial direction, the homogenized material tensor is assumed to be orthotropic, with negligible values for its components E_{1112}^H and E_{2212}^H , which couple normal strains $\varepsilon_{\theta\theta}$ and ε_{zz} with the shear angle $\gamma_{z\theta}$: a not null value for the shear angle $\gamma_{z\theta}$ implies the presence of out-ofplane strains and consequently, a non-uniform stent radial compression which may impact on the crimping and deployment phases. Accordingly, in the cylindrical coordinate system of Fig. 4 the material constitutive relation of Eq. (4) in the plane 1-2 simplifies to

$$\begin{bmatrix} \sigma_{zz} \\ \sigma_{\theta\theta} \\ \tau_{z\theta} \end{bmatrix} = \begin{bmatrix} E_{1111}^H & E_{1122}^H & 0 \\ E_{2211}^H & E_{2222}^H & 0 \\ 0 & 0 & E_{1212}^H \end{bmatrix} \begin{bmatrix} \varepsilon_{zz} \\ \varepsilon_{\theta\theta} \\ \gamma_{z\theta} \end{bmatrix}.$$
(7)

Under an infinitesimal strain assumption, compatibility equations in the cylindrical coordinate system define the normal strains and the shear angle [37]

$$\begin{cases} \varepsilon_{\theta\theta} = \frac{1}{r} \frac{\partial u_{\theta}}{\partial \theta} + \frac{u_{r}}{r} \\ \varepsilon_{zz} = \frac{\partial u_{z}}{\partial z} \\ \gamma_{z\theta} = \frac{\partial u_{z}}{\partial \theta} + \frac{\partial u_{\theta}}{\partial z}, \end{cases}$$
(8)

with u_r , u_θ , u_z the displacement components. Assuming that the axial symmetry of the stent is maintained in the examined loading scenarios (i.e., the cross-sections remain circular and normal to the *z*-axis), Eq. (8) simplifies to

$$\begin{cases} \varepsilon_{\theta\theta} = \frac{u_r}{r} \\ \varepsilon_{zz} = \frac{\partial u_z}{\partial z} \\ \gamma_{\theta z} = \frac{\partial u_{\theta}}{\partial z}. \end{cases}$$
(9)

The derivation of the analytical formulation for the estimate of the mechanical response of the stent is presented in the following subsections.



Fig. 4. Plane stress state in circumferential (θ) and axial (z) directions for the investigated loading scenarios.

2.3.1) Radial stiffness and foreshortening

In the crimping test, the total force exerted by the device in the radial direction (i.e., the radial force) is quantified and used to determine the radial stiffness K_R , expressed as the ratio between the radial force and radial displacement. Radial stiffness is a fundamental mechanical requirement for vascular stents, as they must provide adequate scaffolding for the diseased vessel while minimizing the risk of damaging the arterial tissue [4,6]. Additionally, crimping a vascular stent might involve the elongation of device, which can be evaluated in terms of foreshortening

$$f = \frac{l - l_0}{l_0},\tag{10}$$

where *l* is the stent length when radially compressed and l_0 the device original length (Fig. 2(b)). The foreshortening *f* of the stent should be as small as possible to ensure precise placement during implantation [4,6]. Fig. 3(a) illustrates the boundary conditions prescribed for the radial compression. Specifically, a radial displacement u_r^* is prescribed on the entire cylindrical surface representing the stent. Consequently, the stress along the *z*-direction is identically null and the cylinder elongates at both ends in *z*-direction, reaching a length equal to *l*, with

$$\begin{cases} u_r = u_r^* \\ u_z = \frac{l - l_0}{l_0} \left(z - \frac{l_0}{2} \right), \end{cases}$$
(11)

for $z \in [0, l_0]$. Hence, from Eq. (9), it turns out that

$$\begin{cases} \varepsilon_{\theta\theta} = \frac{u_r^*}{R_0} \\ \varepsilon_{zz} = \frac{l - l_0}{l_0}, \end{cases}$$
(12)

and substituting the expressions for circumferential and axial strains (Eq. 12) into Eq. (7) leads to the expression of the circumferential and axial stresses in terms of components of the homogenized stiffness matrix

$$\begin{cases} \sigma_{\theta\theta} = E_{1122}^H \varepsilon_{zz} + E_{2222}^H \varepsilon_{\theta\theta} \\ \sigma_{zz} = E_{1111}^H \varepsilon_{zz} + E_{1122}^H \varepsilon_{\theta\theta} = 0 \end{cases}$$
(13)

Finally, substituting Eq. (7) in Eq. (12) also allows the expression of foreshortening f in terms of the components of the homogenized stiffness matrix

$$f = \frac{l - l_0}{l_0} = -\frac{E_{1122}^H u_r^*}{E_{1111}^H R_0}.$$
(14)

According to [38,39], the forces F_{θ} (also known as hoop force) and F_r exerted by the vascular stent along the circumferential and the radial direction, respectively, can be expressed

$$F_{\theta} = \sigma_{\theta\theta} l_0 t, \tag{15}$$

$$F_r = 2\pi F_\theta = 2\pi \sigma_{\theta\theta} l_0 t. \tag{16}$$

Therefore, by definition, K_R can be also expressed in terms of components of the homogenized stiffness matrix

$$K_{R} = \frac{F_{r}}{u_{r}^{*}} = \frac{2\pi l_{0} t}{R_{0}} \left(E_{2222}^{H} - \frac{\left(E_{1122}^{H}\right)^{2}}{E_{1111}^{H}} \right) := K_{R}^{M} K_{R}^{m},$$
(17)

14

where

$$\begin{cases} K_R^M = \frac{2\pi l_0 t}{R_0} \\ K_R^m = E_{2222}^H - \frac{\left(E_{1122}^H\right)^2}{E_{1111}^H}, \end{cases}$$
(18)

represent the radial stiffness related to the macroscopic (K_R^M) and microscopic (K_R^m) scales of the stent.

2.3.2) Axial stiffness

The axial stiffness K_A can be evaluated as the ratio between the force exerted by the device in the axial direction (i.e., the axial force) and the imposed axial displacement. Fig. 3(b) illustrates the boundary conditions applied when axial displacement is prescribed to evaluate K_A . Specifically, an axial displacement u_z^* is imposed on one extremity of the cylinder, while the other extremity is fixed in the *z*-direction, namely

$$u_z = \frac{u_z^*}{l_0} z,\tag{19}$$

with $z \in [0, l_0]$. From Eq. (9), it follows that

$$\varepsilon_{ZZ} = \frac{u_Z^*}{l_0}.$$
(20)

Substituting Eq. (20) into Eq. (7) yields the expression of the axial and circumferential stresses in terms of components of the homogenized stiffness matrix

$$\begin{cases} \sigma_{zz} = E_{1111}^H \varepsilon_{zz} + E_{1122}^H \varepsilon_{\theta\theta} \\ \sigma_{\theta\theta} = E_{1122}^H \varepsilon_{zz} + E_{2222}^H \varepsilon_{\theta\theta} = 0, \end{cases}$$

where the stress $\sigma_{\theta\theta}$ is identically null because the cylinder is kept traction-free in the radial direction. Following [38], it turns out that the total axial force F_z can be expressed

$$F_{Z} = \sigma_{ZZ} \pi \left[\left(R_{0} + \frac{t}{2} \right)^{2} - \left(R_{0} - \frac{t}{2} \right)^{2} \right] = \sigma_{ZZ} 2\pi R_{0} t .$$
(21)

Therefore, by definition, K_A can be expressed in terms of the components of the homogenized stiffness matrix

$$K_{A} = \frac{F_{Z}}{u_{Z}^{*}} = \frac{2\pi R_{0} t}{l_{0}} \left(E_{1111}^{H} - \frac{\left(E_{1122}^{H}\right)^{2}}{E_{2222}^{H}} \right) := K_{A}^{M} K_{A}^{m},$$
(22)

where

$$\begin{cases} K_A^M = \frac{2\pi R_0 t}{l_0} \\ K_A^m = E_{1111}^H - \frac{\left(E_{1122}^H\right)^2}{E_{2222}^H}, \end{cases}$$
(23)

represent the axial stiffness related to the macroscopic (K_A^M) and microscopic (K_A^m) scales of the stent.

2.3.3) Torsional stiffness

The torsional stiffness K_T can be evaluated as the ratio between the total torque moment exerted by the device around the axial direction and the imposed rotation around the same direction. Fig. 3(c) illustrates the boundary conditions applied when a rotation around the axial direction is prescribed to evaluate K_T . Specifically, a rotation φ^* is imposed on one extremity of the cylinder, while the other extremity is fixed along the θ -direction, yielding to a circumferential displacement

$$u_{\theta}^* = R_0 \varphi^* \frac{z}{l_0},\tag{24}$$

with $z \in [0, l_0]$. From Eq. (7) and Eq. (9), it follows that

$$\gamma_{\theta z}^* = \frac{R_0}{l_0} \varphi^*, \tag{25}$$

16

$$\tau_{\theta z} = E_{1212}^H \,\gamma_{\theta z}^* \,. \tag{26}$$

As in [38], the torque moment M_z can be expressed in the following terms

$$M_{Z} = \frac{\pi}{2R_{0}} \left[\left(R_{0} + \frac{t}{2} \right)^{4} - \left(R_{0} - \frac{t}{2} \right)^{4} \right] \tau_{\theta Z}.$$
(27)

Therefore, using Eq. (27), the torsional stiffness K_T can be expressed in terms of the components of the homogenized stiffness matrix

$$K_T = \frac{M_z}{\varphi^*} = \frac{\pi (4R_0^3 t + R_0 t^3)}{2l_0} E_{1212}^H := K_T^M K_T^M$$
(28)

where

$$\begin{cases} K_T^M = \frac{\pi (4R_0^3 t + R_0 t^3)}{2l_0} \\ K_T^m = E_{1212}^H, \end{cases}$$
(29)

represent the torsional stiffness related to the macroscopic (K_T^M) and microscopic (K_T^m) scales of the stent.

2.4) Numerical experiments

The analytical formulations derived to express f, K_R , K_A and K_T in terms of the components of the homogenized stiffness matrix are tested against FE simulations where the three loading scenarios are applied to vascular stent designs modelled as cylindrical lattice structures. For this purpose, three stent unit cell types resembling commercially available self-expandable femoral stent designs are considered (Fig. 5(a)). Subsequently, the homogenized stiffness tensor is determined for each one of the three analyzed unit cell designs, and f, K_R , K_A and K_T are evaluated using the derived analytical formulations (Eqs. (14), (17), (22) and (28)). In parallel, FE models of the three vascular stent designs are generated by periodically repeating the unit cells in the axial and circumferential directions (Fig. 5(b)), and f, K_R , K_R

 K_A and K_T are computed based on the FE analysis. Finally, the results from analytical formulations and from FE simulations are compared. The analysis was performed assuming that vascular stents are fabricated from Nickel-Titanium (Young's modulus equal to 60 GPa and Poisson's ratio equal to 0.33 [23]) with the following macroscopic geometrical characteristics: $R_0 = 3.5$ mm, t = 0.1 mm, $N_{\theta} = N_z =$ 20. Furthermore, a sensitivity analysis of the derived analytical formulations with respect to the design parameters N_{θ} and N_z is performed. To address this task, FE models are developed for unit cell type 1 (Fig. 5(a)), covering nine combinations of N_{θ} and N_z , with N_{θ} , $N_z \in [10, 20, 40]$.

2.4.1) Stent unit cell geometries

Fig. 5 displays the three stent designs with different unit cell types selected for the analysis, each resembling commercially available self-expandable femoral stents. Unit cell 1 is inspired by the EverFlex stent (Medtronic, Dublin, Ireland), unit cell 2 by the Zilver PTX stent (Cook Medical, Bloomington, IN, USA), and unit cell 3 by the S.M.A.R.T. Vascular System (S.M.A.R.T., Santa Clara, CA, USA). The unit cells 1, 2 and 3 are assumed to have a unitary height h (Fig. 2(a)) and an aspect ratio α equal to 1.62, 1.28, and 0.73, respectively. For each unit cell, the homogenized stiffness tensor is reconstructed as detailed in Section 2.1.



Fig. 5. (a) Stents unit cells; (b) FE models of stents corresponding to the unit cells in (a), when considering $N_z = N_\theta = 20$, t = 0.1 mm, $R_\theta = 3.5 \text{ mm}$.

2.4.2) FE analysis

FE models for stent mechanical characterization are created starting from the unit cell geometries by using Hypermesh (Altair Engineering, Troy, MI, USA) and Abaqus/Standard (Dassault Systemes Simulia Corp., Johnston, RI, USA). The unit cells (Fig. 5(a)) are meshed with four-nodes shell elements S4R, considering eight elements along the strut width. Grid element size is the result of a mesh grid independence study, detailed in the Supplementary material. Linear structural mechanics FE analysis is carried out adopting the implicit solver Abaqus/Standard, running on 6 computing cores of a workstation equipped with Intel® CoreTM i7-8700 and 32 GB RAM. Boundary conditions for the three distinct loading scenarios (i.e., radial, axial traction, and torsion loading) are applied as described in Fig. 3. Reaction forces and moments are computed to determine K_R , K_A and K_T . Specifically, under the assumption of infinitesimal strains, a value of $u_r^* = 0.25$ mm (Eq. (11)) is assigned for the radial compression scenario, $u_z^* = 0.1$ mm (Eq. (19)) is set for the axial traction scenario, while $\varphi^* = 10^\circ$ (Eq. (24)) is prescribed for the torsion scenario. Additional details regarding the FE analysis are provided in the Supplementary material.

3) Results

3.1) Homogenized stiffness tensor

As the first result, we present the homogenized stiffness tensors for the three stent designs with unit cell types of Fig. 5(a), obtained using the method proposed here:

$$\boldsymbol{E}^{H} = \begin{bmatrix} 428.425 & 38.608 & 0.072 \\ 38.608 & 8.723 & 0.007 \\ 0.072 & 0.007 & 12.472 \end{bmatrix}$$
(MPa), for unit cell 1;
$$\boldsymbol{E}^{H} = \begin{bmatrix} 3615.720 & -0.054 & 0.102 \\ -0.054 & 3.317 & -0.006 \\ 0.102 & -0.006 & 4.734 \end{bmatrix}$$
(MPa), for unit cell 2;
$$\boldsymbol{E}^{H} = \begin{bmatrix} 15.590 & 1.845 & 0.349 \\ 1.845 & 5.367 & -1.090 \\ 0.349 & -1.090 & 3.609 \end{bmatrix}$$
(MPa), for unit cell 3.

Based on the obtained homogenized stiffness tensors, Table 1 summarizes the values of the mechanical response of the stents corresponding to the investigated unit cells, evaluated adopting the analytical formulations derived in Section 2.3. From the analysis it emerges that while the values of the radial and the torsional stiffness at the micro-scale are of the same order of magnitude for the three cell unit types, the axial stiffness varies considerably, from 15.0 MPa (unit cell type 3) to 3615.7 MPa (unit cell type 2).

Additionally, the stent made by unit cells type 2 demonstrates auxetic properties, with a negative, near zero value of f, markedly lower compared to the other stents.

Table 1. Mechanical response of the stents associated with the three stent designs with different unit cell types in Fig. 5(a), evaluated using the derived analytical formulations considering $N_{\theta} = N_z = 20$, $R_{\theta} = 3.5$ mm, and t = 0.1 mm.

				Rad	dial crimp	oing	Axial traction			Torsion		
	a	l_0	f	K_R^m	K_R^M	K_R	K_A^m	K^M_A	K_A	K_T^m	K_T^M	K_T
	ū	(mm)	(%)	(MPa)	(mm)	(N/mm)	(MPa)	(mm)	(N/mm)	(MPa)	(mm ²)	(N mm)
Stent 1	1.62	35.6	6.1	5.2	6.39	33.5	257.5	0.06	15.7	12.5	0.77	9.4
Stent 2	1.28	28.1	-10-4	3.3	5.04	16.8	3615.7	0.08	278.4	4.7	0.98	4.5
Stent 3 (0.73	16.1	0.85	5.2	2.89	14.8	15.0	0.14	2.0	3.6	1.71	6.1

 α : aspect ratio of the unit cell; K_R^m : radial stiffness of the stent at the micro-scale; K_R^M : radial stiffness of the stent at the macro-scale; K_R : radial stiffness of the stent; K_A^m : axial stiffness of the stent at the micro-scale; K_A^m : axial stiffness of the stent; K_T^m : torsional stiffness of the stent at the micro-scale; K_A^m : axial stiffness of the stent; K_T^m : torsional stiffness of the stent.

3.2) Derived analytical formulations vs. FE analysis

The paired comparison between the values of f, K_R , K_A and K_T , as evaluated using the derived analytical formulations and the FE analysis, is summarized in Fig. 6 for the three different unit cell typesbased devices. A satisfactory agreement emerges between the two sets of values. Specifically, the relative differences between the analytical formulation and the FE analysis are up to 6 % for K_R ([3 % - 6 %]) and up to 4 % for K_A ([2 % - 4 %]). As for K_T , differences up to 18 % emerge ([2 % - 18 %]). The largest deviation is observed for the foreshortening f, with differences less than 6 % for stents with unit cell types 1 and 3, but up to 49 % for the device relative to unit cell type 2, which is attributed to the very small value obtained for f, which is close to zero ($f = -10^{-4}$ %).



Fig. 6. Values of (a) f, (b) K_R , (c) K_A and (b) K_T computed using the derived analytical formulations as well as by FE analysis for the investigated stents, made of three different unit cell types. f: foreshortening; K_R : radial stiffness; K_A : axial stiffness; K_T : torsional stiffness; N_z and N_θ : number of repetitions of the unit cell in z and θ directions, respectively. For the sake of comparison, vascular stents were considered with the following macroscopic geometrical characteristics: $R_0 = 3.5$ mm, t = 0.1mm, $N_\theta = N_z = 20$.

The results of the sensitivity analysis for f, K_R , K_A , and K_T , evaluated using the derived analytical formulations, with respect to the geometric parameters N_z and N_θ are presented in Fig. 7 for the stent design based on the unit cell type 1, accompanied by the paired values from the FE analysis. Overall, a close agreement emerges across the considered ranges of variations for N_z and N_θ , between values obtained from the analytical formulations and those derived from the 3D FE models. Specifically, relative differences are approximately 6 % and 3 % for f and K_A , respectively (Fig. 7(a) and (c)). Regarding the calculation of K_R , the relative difference is reduced from approximately 6 % to 2 % when increasing N_θ from 10 to 40, for all the N_z values (Fig. 7(b)). Finally, regarding the calculation of K_T , the relative difference decreases from approximately 19 % to 5 %, from 17 % to 5 %, and from 16 % to 4 %, by varying N_z from 10 to 40, for $N_{\theta} = 10$, $N_{\theta} = 20$, and $N_{\theta} = 40$, respectively (Fig. 7(d)).



Fig. 7. Values of (a) f, (b) K_R , (c) K_A and (d) K_T evaluated using the derived analytical formulations along with the corresponding values provided by the FE analysis for the stent design corresponding to unit cell type 1, when considering different values of N_z and N_{θ} . f: foreshortening; K_R : radial stiffness; K_A : axial stiffness; K_T : torsional stiffness. N_z and N_{θ} : number of repetitions of the unit cell in z and θ direction, respectively. For the sake of comparison, vascular stents were assumed to have the following macroscopic geometrical characteristics: $R_{\theta} = 3.5$ mm and t = 0.1 mm.

4) Discussion

Computational models have proven to be efficient tools for assisting the design phase of vascular stents, enabling the optimization of the mechanical response, with the ultimate goal of enhancing treatment safety and efficiency [6,13-29]. In this context, the present study contributes to the advancement of vascular stent design and performance analysis by exploring the relationship between stent unit cell attributes and stent mechanical response, thereby facilitating the optimization of the mechanical performance. The analytical formulations derived here effectively describe the mechanical behavior of the stent through a combination of stiffness matrix components obtained using a throughscales homogenization strategy. The proposed method promises to become an easy-to-use, automated tool supporting stents design and optimization, reducing the need for expensive 3D structural mechanics simulations. This is achieved by performing homogenization analysis on the 2D unit cell, which has already been proven to be fully automatable. In this regard, starting from an imported unit cell geometry, the overall procedure takes less than 5 minutes to evaluate the mechanical behavior of the stent on a standard laptop (Intel^(R) CoreTM i7-1165G7 and 8 GB RAM). Thus, the procedure is well-suited for integration into computational optimization frameworks. In particular, shape optimization frameworks for vascular stents typically consider an initial geometry with a set of parameterized geometric features, which are explored within the design space to enhance the device's mechanical performance [6]: the proposed procedure can be adopted to automatically evaluate a set of unit cells, or it can be incorporated in the optimization iterative routine to link the geometrical attributes of the unit cell to optimization objectives (Fig. 8). Additionally, topology optimization frameworks for vascular stents generally aim to iteratively determine the optimal material distribution to meet specific design requirements without relying on an initial predefined stent geometry, resulting in a more general approach with the potential to generate innovative geometries [6]. Specifically, a recent study [23] has exploited topology optimization for designing innovative stent unit cells that match specific values of homogenized stiffness tensor components. The capability of this framework can be extended to link f, K_R , K_A , and K_T of the stent with the homogenized material tensor, enabling the generation of optimal unit cell geometries that meet specific mechanical requirements (Fig. 8).

The derived analytical formulations for f, K_R , K_A and K_T have been successfully tested against FE simulations considering three different stent unit cell designs resembling commercial devices. The major observed discrepancies can be ascribed to approximations related to the homogenization of the lattice structure, as shown in Fig. 7, where relative differences are reduced as the number of repetitions of the unit cell along the radial and the axial directions increases.

The analysis of the homogenized stiffness tensors in Eqs. (14), (17), (22) and (28) reveals important insights into the mechanical performance of the corresponding stents. For unit cell types 1 and 2, the components E_{1112}^H and E_{2212}^H are close to zero and markedly lower than E_{1111}^H , E_{2222}^H and E_{1212}^H . This suggests that cells 1 and 2 exhibit approximately orthotropic material behavior, where normal and shear stress/strain coupling is negligible. Moreover, for unit cell type 2, the value of the component E_{1122}^H is close to zero, indicating a negligible coupling between normal stress/strain in circumferential and axial directions. Furthermore, since stiffness matrix components E_{1122}^H and E_{1111}^H have opposite sign, the foreshortening *f* is negative during radial compression, with the stent exhibiting an auxetic behavior (Eq. (14)). This feature is consistent with the study in [40] where a similar geometry is examined and classified as auxetic. Concerning unit cell type 3, component E_{1112}^H is negligible, whereas E_{2212}^H is of comparable magnitude with respect to E_{1111}^H , E_{2222}^H , and E_{1212}^H . This suggests a potential coupling between normal and shear stress/strains, which may lead to irregular closure of the stent during radial compression.

This study presents some limitations. The equations used to characterize the mechanical behavior of the stents are formulated under the assumption of linear elasticity. While this assumption has enabled the development of a rapid and automated method that can be easily integrated into different computational frameworks, it does not account for the large deformations experienced by the devices during crimping and subsequent expansion, and thus for geometric and material nonlinearity effects. Although, once the optimal configuration for the unit cell is identified, a posteriori nonlinear FE simulations can be conducted to provide a complete mechanical characterization of the devices [23]. Furthermore, the method is developed by assuming the periodic repetition of the unit cell along the axial and circumferential direction of the stent, but vascular stents may feature a different periodic arrangement of links for axial connections of the unit cells, where not all unit cells are axially connected. While the specific periodic arrangement of the axial links may have a negligible impact on the stent radial stiffness [41], it could affect foreshortening, axial and torsional stiffness [42,43]. Lastly, only three loading scenarios were investigated. Other loading scenarios, such as bending or more complex loading conditions, could be considered. However, it is not guaranteed that under these loading conditions, the assumption of axial symmetry for the definition of the analytical relationships is applicable.



Fig. 8. Implementation of the proposed approach within stent optimization frameworks.

5) Conclusions

This study introduces a rapid and automated method based on homogenization theory for the derivation of analytical formulations for the assessment of the mechanical response of vascular stents starting from the associated unit cell topology. The method, successfully tested against FE simulations conducted on three stent designs with different unit cell types inspired to commercial vascular stents, proved to be accurate. The derived analytical formulations enable easy comparisons of the mechanical response of diverse stent designs under specific loading conditions (i.e., radial, axial traction and torsion loadings), and is well-suited for integration into several computational frameworks, including optimization frameworks. Overall, the presented approach has the potential to facilitate and refine the stent development process, reducing the time and costs associated with the iterative development and prototyping phases.

Funding

This study was carried out within the project "RESET: Rethinking femoral artery Stents for the trEatment of lower-limb peripheral arTery disease", funded by the European Union – NextGenerationEU, Italian Ministry of University and Research, Italy, within the PRIN 2022 PNRR program (D.D.1409 del 14/09/2022). FM acknowledges the support of the research fund FAR 2023 DIP - Fondo di Ateneo per la Ricerca per il finanziamento di progetti di ricerca dipartimentali (Department of Engineering "Enzo Ferrari", University of Modena and Reggio Emilia) and participates to the GNCS project MOMENTI - MOdelli e MEtodi Numerici per il Trattamento delle Immagini (Gruppo Nazionale per il Calcolo Scientifico - Istituto Nazionale di Alta Matematica "Francesco Severi"). NF and SP acknowledge the support by MUR, grant Dipartimento di Eccellenza 2023–2027. NF acknowledges the INdAM–GNCS 2024 Project "Accuratezza geometrica e adattività di griglia per problemi con interfacce complesse".

Acknowledgements

None.

Declaration of Competing Interest

The authors declare that they have no conflict of interest.

CRediT author statement

Dario Carbonaro: Conceptualization, Methodology, Software, Validation, Investigation, Formal analysis, Data curation, Visualization, Writing – original draft, Writing – review & editing.

Nicola Ferro: Methodology, Investigation, Data curation, Writing – original draft, Writing – review & editing.

Francesco Mezzadri: Methodology, Funding acquisition, Writing – original draft, Writing – review & editing.

Diego Gallo: Methodology, Supervision, Writing – review & editing.

Alberto Luigi Audenino: Resources, Supervision, Writing - review & editing.

Simona Perotto: Methodology, Funding acquisition, Supervision, Writing – review & editing.

Umberto Morbiducci: Conceptualization, Methodology, Supervision, Writing – review & editing.

Claudio Chiastra: Conceptualization, Methodology, Supervision, Project administration, Funding acquisition, Writing – original draft, Writing – review & editing.

Bibliography

- S. Borhani, S. Hassanajili, S.H. Ahmadi Tafti, S. Rabbani, Cardiovascular stents: overview, evolution, and next generation, Prog. Biomater. 7 (2018) 175–205. https://doi.org/10.1007/s40204-018-0097-y.
- T.W. Duerig, M. Wholey, A comparison of balloon- and self-expanding stents, Min Invas Ther
 Allied Technol. 11 (2002) 173–178. https://doi.org/10.1080/136457002760273386.
- [3] W. Jiang, W. Zhao, T. Zhou, L. Wang, T. Qiu, A review on manufacturing and post-processing technology of vascular stents, Micromachines. 13 (2022) 140.
 https://doi.org/10.3390/mi13010140.
- [4] C. Pan, Y. Han, J. Lu, Structural design of vascular stents: A review, Micromachines. 12 (2021)
 1–26. https://doi.org/10.3390/mi12070770.
- [5] B. Polanec, J. Kramberger, S. Glodež, A review of production technologies and materials for manufacturing of cardiovascular stents, Adv. Prod. Eng. Manag. 15 (2020) 390–402. https://doi.org/10.14743/APEM2020.4.373.
- [6] A. Kapoor, N. Jepson, N.W. Bressloff, P.H. Loh, T. Ray, S. Beier, The road to the ideal stent: A review of stent design optimisation methods, findings, and opportunities, Mater. Des. 237 (2024) 112556. https://doi.org/10.1016/j.matdes.2023.112556.
- [7] D. Carbonaro, E. Villa, D. Gallo, U. Morbiducci, A.L. Audenino, C. Chiastra, Designing the mechanical behavior of NiTi self-expandable vascular stents by tuning the heat treatment parameters, J. Mech. Behav. Biomed. Mater. 158 (2024) 106653.

https://doi.org/https://doi.org/10.1016/j.jmbbm.2024.106653.

- [8] A. García, E. Peña, M.A. Martínez, Influence of geometrical parameters on radial force during self-expanding stent deployment. Application for a variable radial stiffness stent, J. Mech.
 Behav. Biomed. Mater. 10 (2012) 166–175. https://doi.org/10.1016/j.jmbbm.2012.02.006.
- [9] F.D. Whitcher, Simulation of in vivo loading conditions of nitinol vascular stent structures, Comput. Struct. 64 (1997) 1005–1011. https://doi.org/10.1016/S0045-7949(97)00014-X.
- [10] A. Fortier, V. Gullapalli, R.A. Mirshams, Review of biomechanical studies of arteries and their effect on stent performance, IJC Hear. Vessel. 4 (2014) 12–18.
 https://doi.org/10.1016/j.ijchv.2014.04.007.
- K. Maleckis, P. Deegan, W. Poulson, C. Sievers, A. Desyatova, J. MacTaggart, A. Kamenskiy, Comparison of femoropopliteal artery stents under axial and radial compression, axial tension, bending, and torsion deformations, J. Mech. Behav. Biomed. Mater. 75 (2017) 160–168. https://doi.org/10.1016/j.jmbbm.2017.07.017.
- T.M. Morrison, M.L. Dreher, S. Nagaraja, L.M. Angelone, W. Kainz, The role of computational modeling and simulation in the total product life cycle of peripheral vascular devices, J. Med. Devices, Trans. ASME. 11 (2017) 1–10. https://doi.org/10.1115/1.4035866.
- [13] G. Alaimo, F. Auricchio, M. Conti, M. Zingales, Multi-objective optimization of nitinol stent design, Med. Eng. Phys. 47 (2017) 13–24. https://doi.org/10.1016/j.medengphy.2017.06.026.
- W. Wu, D.Z. Yang, Y.Y. Huang, M. Qi, W.Q. Wang, Topology optimization of a novel stent platform with drug reservoirs, Med. Eng. Phys. 30 (2008) 1177–1185.
 https://doi.org/10.1016/j.medengphy.2008.02.010.
- [15] W. Wu, L. Petrini, D. Gastaldi, T. Villa, M. Vedani, E. Lesma, B. Previtali, F. Migliavacca,

Finite element shape optimization for biodegradable magnesium alloy stents, Ann. Biomed. Eng. 38 (2010) 2829–2840. https://doi.org/10.1007/s10439-010-0057-8.

- [16] H. Xue, S.C. Saha, S. Beier, N. Jepson, Z. Luo, Topological optimization of auxetic coronary stents considering hemodynamics, Front. Bioeng. Biotechnol. 9 (2021) 1–17. https://doi.org/10.3389/fbioe.2021.728914.
- [17] H. Xue, Z. Luo, T. Brown, S. Beier, Design of self-expanding auxetic stents using topology optimization, Front. Bioeng. Biotechnol. 8 (2020) 1–16.
 https://doi.org/10.3389/fbioe.2020.00736.
- [18] D. Carbonaro, A. Lucchetti, A.L. Audenino, T. Gries, T.J. Vaughan, C. Chiastra, Multi-objective design optimization of bioresorbable braided stents, Comput. Methods Programs Biomed. 242 (2023) 107781. https://doi.org/10.1016/j.cmpb.2023.107781.
- [19] J.B. Russ, R.L. Li, A.R. Herschman, H. Waisman, V. Vedula, J.W. Kysar, D. Kalfa, Design optimization of a cardiovascular stent with application to a balloon expandable prosthetic heart valve, Mater. Des. 209 (2021) 109977. https://doi.org/10.1016/j.matdes.2021.109977.
- [20] D. Carbonaro, D. Gallo, U. Morbiducci, A. Audenino, C. Chiastra, In silico biomechanical design of the metal frame of transcatheter aortic valves: multi-objective shape and crosssectional size optimization, Struct. Multidiscip. Optim. 64 (2021) 1825–1842. https://doi.org/10.1007/s00158-021-02944-w.
- [21] D. Carbonaro, S. Zambon, A. Corti, D. Gallo, U. Morbiducci, L. Audenino, C. Chiastra, Impact of nickel – titanium super-elastic material properties on the mechanical performance of selfexpandable transcatheter aortic valves, J. Mech. Behav. Biomed. Mater. 138 (2023) 105623. https://doi.org/10.1016/j.jmbbm.2022.105623.

- [22] S. Čanić, L. Grubišić, D. Lacmanović, M. Ljulj, J. Tambača, Optimal design of vascular stents using a network of 1D slender curved rods, Comput. Methods Appl. Mech. Eng. 394 (2022) 1–32. https://doi.org/10.1016/j.cma.2022.114853.
- [23] D. Carbonaro, F. Mezzadri, N. Ferro, G. De Nisco, A.L. Audenino, D. Gallo, C. Chiastra, U.
 Morbiducci, S. Perotto, Design of innovative self-expandable femoral stents using inverse homogenization topology optimization, Comput. Methods Appl. Mech. Eng. 416 (2023) 116288. https://doi.org/10.1016/j.cma.2023.116288.
- [24] R. Clune, D. Kelliher, J.C. Robinson, J.S. Campbell, NURBS modeling and structural shape optimization of cardiovascular stents, Struct. Multidiscip. Optim. 50 (2014) 159–168. https://doi.org/10.1007/s00158-013-1038-y.
- [25] K.A. James, H. Waisman, Layout design of a bi-stable cardiovascular stent using topology optimization, Comput. Methods Appl. Mech. Eng. 305 (2016) 869–890.
 https://doi.org/10.1016/j.cma.2016.02.036.
- [26] N.S. Ribeiro, J. Folgado, H.C. Rodrigues, Surrogate-based multi-objective design optimization of a coronary stent: Altering geometry toward improved biomechanical performance, Int. j. Numer. Method. Biomed. Eng. 37 (2021) 1–24. https://doi.org/10.1002/cnm.3453.
- [27] H.X. Li, W.L. Shi, Z. Tan, M.J. Wang, D.Y. Zhao, J. Yan, Topology optimization for polymeric stent, Struct. Multidiscip. Optim. 65 (2022) 1–13. https://doi.org/10.1007/s00158-022-03292-z.
- S. Pant, G. Limbert, N.P. Curzen, N.W. Bressloff, Multiobjective design optimisation of coronary stents, Biomaterials. 32 (2011) 7755–7773.
 https://doi.org/10.1016/j.biomaterials.2011.07.059.
- [29] S. Pant, N.W. Bressloff, G. Limbert, Geometry parameterization and multidisciplinary

constrained optimization of coronary stents, Biomech. Model. Mechanobiol. 11 (2012) 61–82. https://doi.org/10.1007/s10237-011-0293-3.

- [30] A. Bensoussan, J.-L. Lions, G. Papanicolaou, Asymptotic Analysis for Periodic Structures, 2011. https://doi.org/10.1090/chel/374.
- [31] E. Andreassen, C.S. Andreasen, How to determine composite material properties using numerical homogenization, Comput. Mater. Sci. 83 (2014) 488–495.
 https://doi.org/10.1016/j.commatsci.2013.09.006.
- [32] N. Ferro, S. Perotto, D. Bianchi, R. Ferrante, M. Mannisi, Design of cellular materials for multiscale topology optimization: application to patient-specific orthopedic devices, Struct.
 Multidiscip. Optim. 65 (2022) 79. https://doi.org/10.1007/s00158-021-03163-z.
- [33] M. Gavazzoni, N. Ferro, S. Perotto, S. Foletti, Multi-physics inverse homogenization for the design of innovative cellular materials: Application to thermo-elastic problems, Math. Comput. Appl. 27 (2022) 15. https://doi.org/10.3390/mca27010015.
- [34] N. Ferro, S. Micheletti, S. Perotto, Density-based inverse homogenization with anisotropically adapted elements, in: Lect. Notes Comput. Sci. Eng., Springer, 2020: pp. 211–221. https://doi.org/10.1007/978-3-030-30705-9_19.
- [35] ISO, Cardiovascular implants Endovascular devices Part 2: Vascular stents, (2012).
- [36] FDA, Non-clinical engineering tests and recommended labeling for intravascular stents and associated delivery systems, (2010).
- [37] G. Qi, C.X. Liu, K. Feng, L. Ma, K.U. Schröder, Analytical solutions of stress distribution within a hollow cylinder under contact interactions, Int. J. Mech. Sci. 239 (2023) 107897. https://doi.org/10.1016/j.ijmecsci.2022.107897.

- [38] F.P. Beer, R. Johnston, J. Dewolf, D. Mazurek, Mechanics of Materials, McGraw-Hill, 2013.
- [39] M.S. Cabrera, C.W.J. Oomens, F.P.T. Baaijens, Understanding the requirements of selfexpandable stents for heart valve replacement: Radial force, hoop force and equilibrium, J.
 Mech. Behav. Biomed. Mater. 68 (2017) 252–264. https://doi.org/10.1016/j.jmbbm.2017.02.006.
- [40] R. Vellaparambil, W. Han, P. Di Giovanni, S. Avril, Experimental validation of auxetic stent designs: three-point bending of 3D printed Titanium prototypes, 6 (2024) 1388207.
 https://doi.org/10.3389/fmedt.2024.1388207.
- [41] M. Azaouzi, A. Makradi, S. Belouettar, F. Auricchio, R.L. Taylor, J. Lubliner, Numerical investigations of the structural behavior of a balloon expandable stent design using finite element method, Comput. Methods Appl. Mech. Eng. 72 (1997) 281–312. https://doi.org/10.1016/j.commatsci.2013.01.031.
- [42] X. Shen, K. Lu, H. Zhu, J. Jiang, R. Tian, H. Li, Torsional behavior of stents: The role of linker and stent tapering investigated with numerical simulation, J. Mech. Med. Biol. 22 (2022) 2250038. https://doi.org/10.1142/S0219519422500385.
- [43] A. Qiao, Z. Zhang, Solid and fluid simulations of vertebral artery stenosis treated with stents with different shapes of link, Appl. Mech. Mater. 553 (2014) 041007.
 https://doi.org/10.4028/www.scientific.net/AMM.553.338.

MOX Technical Reports, last issues

Dipartimento di Matematica Politecnico di Milano, Via Bonardi 9 - 20133 Milano (Italy)

58/2024 Ciaramella, G.; Vanzan, T. Variable reduction as a nonlinear preconditioning approach for optimization problems

> Speroni, G.; Ferro, N. A novel metric-based mesh adaptation algorithm for 3D periodic domains

Temellini, E.; Ferro, N.; Stabile, G.; Delgado Avila, E.; Chacon Rebollo, T.; Perotto, S. *Space-time mesh adaptation for the VMS-Smagorinsky modeling of high Reynolds number flows*

- **57/2024** Negrini, G.: Parolini, N.; Verani, M. An Immersed Boundary Method for Polymeric Continuous Mixing
- **56/2024** Parolini, N.; Covello, V.; Della Rocca, A.; Verani, M., Design of a checkerboard counterflow heat exchanger for industrial applications
- **55/2024** Artoni, A.; Ciaramella, G.; Gander, M.J.; Mazzieri, I. Schwarz Waveform Relaxation and the Unmapped Tent-Pitching Method in 3D
- 54/2024 Antonietti, P.F.; Botti, M.; Cancrini, A.; Mazzieri, I.A polytopal discontinuous Galerkin method for the pseudo-stress formulation of the unsteady Stokes problem
- **53/2024** Caldana, M.; Hesthaven, J. S. Neural ordinary differential equations for model order reduction of stiff systems

Negrini, G.; Parolini, N.; Verani, M. Immersed Boundary Method for Polymeric Continuous Mixing

52/2024 Botti, M.; Mascotto, L.
 A Necas-Lions inequality with symmetric gradients on star-shaped domains based on a first order Babuska-Aziz inequality